

# Mechanical Properties of Internal Curing Of Concrete Using Light Weight Aggregates

Mr.R.Gowrishankar,

Department of Civil Engineering,

PGP college of Engineering and Technology

Namakkal, Tamilnadu, India.

gowricivil@gmail.com

Contact no. +91-9750236832

**Abstract** - The present paper discusses the experimental studies of internal curing of concrete using light expanded clay (LECA) and vermiculite. Water is an essential component for cement hydration which can be gained with proper curing. Under practical situations, many structures do not allow curing with water after the construction. In such a case often curing compounds are used to avoid loss of water from the concrete. However it is not sufficient for continuous hydration of cement. In this respect, the porosity of light weight aggregate provide source of water for internal curing of concrete which can provide continued enhancement of concrete strength and durability. For this reason, fine aggregate is replaced by 5% and 10% of LWA in the mix to find its enhancement of internal curing in this study. The properties studied reveal that incorporation of LWA does not have remarkable change in mechanical properties.

**Keywords**- Internal curing, Plastic Shrinkage, Workability, Water Absorption, Vermiculite, LECA

## I. INTRODUCTION

In the 21<sup>st</sup> century, internal curing has emerged as a new technology that holds promise for producing concrete with increased resistance to early-age cracking and enhanced durability. Since concrete service life is a key component of providing a sustainable infrastructure, internal curing can provide a positive contribution to increasing the sustainability of our nation's infrastructure.

Internal water curing has a significant effect on concrete. In addition to affecting hydration and moisture distribution, it influences most concrete properties, such as shrinkage, cracking, and durability. In 2010, the American Concrete Institute (ACI) defined internal curing in its ACI Terminology Guide as "supplying water throughout a freshly placed cementitious mixture using reservoirs, via pre-wetted lightweight aggregates, that readily release water as needed for hydration or to replace moisture lost through evaporation".

Internal curing refers to the process by which the hydration of cement occurs because of the availability of additional internal water that is not part of the mixing water. The additional water being supplied by using relatively small amounts of saturated light weight fine aggregates in concrete [1].

Internal curing works by supplying water from the pre-wetted lightweight aggregate (LWA) to fill in the voids created by chemical shrinkage [2, 3]. Internal curing has been shown in the laboratory to be

quite effective as a mitigation strategy for self-desiccation and autogenous shrinkage [4, 5]. More recent findings have also shown that in addition to reducing shrinkage, internal curing can reduce shrinkage cracking [6], reduce plastic shrinkage cracking [7] and reduce water absorption [8].

Aim of the paper is to find the performance of light weight aggregates (LECA and Vermiculite) as 5% and 10% replacement of fine aggregate as self curing agent. The use of self curing aggregate is very important from the point of view that water resources are getting valuable every day more over requirement of water for concreting is also high. (ie.,) 1m<sup>3</sup> of concrete requires 3 m<sup>3</sup> of water for construction, most of which is needed for curing. At present, the benefit of self curing agent is realized in desert areas and dry seasons of dry areas and soon may be felt in all areas.

## II. MATERIALS

- Ordinary Portland Cement (53 grade) conforming to IS: 12269 was used. The physical and chemical properties of cement are presented in Table 1 & 2.
- Locally available river sand was used as one of the constituent in the present work. The properties of the sand were studied in accordance with IS 2386-1963 and the results are given in Table 3.
- Light Expanded Clay Aggregate (LECA) and Vermiculite were used to provide internal curing

agent in this study. The LECA is produced by baking pure natural clay in rotary kiln at about 1200 degree centigrade. Vermiculite is a natural mineral that expands with the application of heat. Vermiculite is formed by hydration of certain basaltic minerals. The properties of LECA and vermiculite are given in Table 4.

- Locally available coarse aggregate having maximum size 20 mm was used in the present work. The physical properties of coarse aggregates were measured in accordance with IS 2386-1963 and the results are presented in Table 3.
- Water used for this study is the potable water available in K.S.R. College of Engineering campus, Tiruchengode.

Table-1 Physical properties of cement

S.No	Properties	Observed values
1.	Standard Consistency	33%
2	Initial setting time	30 minutes
3	Final setting time	600 minutes
4.	Compressive Strength	54.08 N/mm <sup>2</sup>
5.	Fineness by sieving	6%
6.	Specific Gravity	3.1

Table-2 Chemical properties of cement

S.No	Properties	Observed Values (%)
1.	CaO	63.8
2.	SiO <sub>2</sub>	21.4
3.	Al <sub>2</sub> O <sub>3</sub>	5.1
4.	Fe <sub>2</sub> O <sub>3</sub>	2.6
5.	MgO	0.36
6.	SO <sub>3</sub>	3.38
7.	Insoluble Residue	0.8
8.	Loss On Ignition	1.6
9.	K <sub>2</sub> O	1.88
10.	Na <sub>2</sub> O	0.14

Table-3 Properties of river sand and coarse aggregate

S.No	Properties	River Sand	Coarse Aggregate
1.	Specific Gravity	2.7	2.8
2.	Bulk density	1510 kg/m <sup>3</sup>	1540 kg/m <sup>3</sup>
3.	Water absorption test	0.51%	0.302%
4.	Fineness Modulus	3.28(Zone III)	8.27

Table-4 Properties of leca and vermiculite

S.No	Properties	LECA	Vermiculite
1.	Specific gravity	1.78	1.826
2.	Fineness Modulus	4.60 (zone I)	4.736 (zone I)
3.	Water absorption test (24 hrs soaking)	29.4%	18.4%
4.	Water absorption test (24 hrs soaking & 5 hrs heating)	86.2%	71.7%
5.	Porosity test	85.38%	26%

### III. MIX PROPORTION

The concrete mix design was done as per IS: 10262-2009. Control Mix M30 grade concrete without light weight aggregate was used. The proportions for the concrete, as determined were 1:1.2:2.4 with water cement ratio of 0.4 by weight. The other concrete mixtures were made by replacing fine aggregate with 5% & 10% LECA and 5%, & 10% vermiculate. The quantities of each mix proportion are listed in Table 5.

### IV. PREPARATION AND TESTING OF SPECIMENS

- Fresh concrete and dry concrete density were measured at the fresh state as well as at hardened state.
- The workability of concrete was measured with slump cone and with compaction factor apparatus.
- Cube moulds of 150 mm were used for compression testing of concrete. Cubes were tested at the age of 7 days curing using compression testing machine as per IS: 516-1959.
- The beam specimens of size 500 mm length, 100 mm breadth, 100 mm height were used to

determine the flexural strength of concrete at the age of 28 days as per IS : 516 -1959.

Table-5 Mix proportions of internal curing concrete

S. No	Material	Quantity kg/m <sup>3</sup>		
		Control mix 0%	5% LECA/ Vermiculite	10% LECA/ Vermiculite
1.	Cement	492.5	492.5	492.5
2.	Fine aggregate (Sand)	594	564.3	534.6
3.	LECA/ Vermiculite	-	29.7	59.4
4.	Coarse aggregate	1195	1195	1195
5.	Water	197	197	197

- Splitting tensile strength tests were carried out on cylinder specimens of size 150 mm diameter and 300 mm length at the age of 7 days as per IS : 5816 - 1970.
- The cylinder specimens of size 150 mm diameter and 300 mm height were used to determine the modulus of elasticity of concrete in compression at the age.
- Specimens demoulded after 24 hours were kept in open atmosphere in order to study the effect of internal curing except for control concrete.

## V. RESULTS AND DISCUSSIONS

- A. Fresh concrete properties of internal curing of concrete
- The slump value and compaction factor for the mixes with LECA and Vermiculite are given in Table 6. The values remain almost same for the mixes studied. Incorporation of LECA and Vermiculite as internal curing agent does not have any effect on slump value and compaction factor.
  - The fresh concrete and hardened concrete density is put into a Table 7. Addition of LECA and Vermiculite plays a role in reducing the density at fresh as well as at hardened state of concrete. As anticipated, the density is reduced with increase in quantity of LECA and Vermiculite due its low density.

Table-6 Internal curing concrete fresh properties

S.No	Mix	Slump Value (mm)	Compaction Factor
1.	0%	28	0.89
2.	5% LECA	29	0.89
3.	10% LECA	29	0.9
4.	5% Vermiculite	29	0.9
5.	10% Vermiculite	28.5	0.9

Table-7 Density of internal curing of concrete

S.No	Mix	Fresh Concrete Density (kg/m <sup>3</sup> )	Hardened Concrete Density (kg/m <sup>3</sup> )
1.	0%	3080	1600
2.	5% LECA	2480	1300
3.	10% LECA	2780	1000
4.	5% Vermiculite	2480	1300
5.	10% Vermiculite	2780	1000

Table-8 7 days compressive strength and splitting tensile strength of internal curing concrete

S.No	Mix	Compressive Strength MPa	Splitting Tensile Strength MPa
1.	0%	41.52	5.76
2.	5% LECA	32.5	2.6
3.	10% LECA	33.5	2.62
4.	5% Vermiculite	33	2.75
5.	10% Vermiculite	33.6	2.78

- B. Hardened concrete properties of internal curing of concrete

The hardened concrete properties such as compressive strength, split tensile strength, flexural strength and E-value of internal curing of concrete are presented in Table 8 & 9. The compressive strength and split tensile strength of mixes containing

LECA and Vermiculite are found to be less than that of control mix. However, it was higher than design strength. Further, similar observations were not made in flexural strength and E-value of internal curing of concrete while comparing with control mix. No variation in compressive strength and split tensile strength was observed among two LWAs and control mix. In general, no variation in strength properties was observed between LECA and Vermiculite.

**Table-9 7 days flexural strength and e-value of Internal curing concrete**

S.No	Mix	Flexural Strength MPa	E-VALUE MPa
1.	0%	6.62	$0.25 \times 10^5$
2.	5% LECA	6.8	$0.24 \times 10^5$
3.	10% LECA	7	$0.25 \times 10^5$
4.	5% Vermiculite	6.7	$0.24 \times 10^5$
5.	10% Vermiculite	6.64	$0.25 \times 10^5$

## VI. CONCLUSION

The following conclusions are drawn from the study

- Partial replacement of fine aggregate, by saturated light weight aggregate, LECA and Vermiculite had no effect on the workability of concrete
- Density of LWA concrete had significant effect in comparison with control mix without LWA
- Internal curing with prewetted LWA influenced the mechanical properties of concrete. The compressive strength and split tensile strength of LWA was less than the control mix with no LWA.
- No remarkable variation was obtained in flexural strength and E-value of internal curing of concrete.

## REFERENCES

- [1] Bentz .D.P., Lura .P ; Roberts J.W., Mixture proportioning for Internal curing concrete International , Vol 27, No 2, 35 - 40, Feb 2005.\
- [2] O. Arioiz, K.Kilinc1, B. Karasu, G. Kaya, G. Arslan, M. Tuncan, A. Tuncan, M. Korkut and S. Kivrak., A Preliminary Research on the Properties of Lightweight Expanded Clay Aggregate, J. Aust. Ceram. Soc. 44 [1] (2008) 23-30.
- [3] Lura, P., O. Jensen, and S.-I. Igarashi, Experimental observation of internal water curing of concrete, Materials and Structures, 2007. 40(2): pp. 211-220.
- [4] Bentz, D.P., P.M. Halleck, A.S. Grader, and J.W. Roberts, Water movement during internal curing: Direct observation using x-ray microtomography, Concrete International, 2006. 28(10): pp. 39-45.
- [5] Jensen, O.M. and P.F. Hansen, Autogenous deformation and rh-change in perspective, Cement and Concrete Research, 2001. 31(12): pp. 1859-1865.
- [6] Lura, P., D. Bentz, D. Lange, K. Kovler, A. Bentur, and K. van Breugel, Measurement of water transport from saturated pumice aggregates to hardening cement paste, Materials and Structures, 2006. 39(9): pp. 861-868. Henkensiefken, Nantung and Weiss LWC Bridges Workshop 2009 IBC 13.
- [7] Henkensiefken, R., T. Nantung, D.P. Bentz, and J. Weiss, Volume change and cracking in internally cured mixtures made with saturated lightweight aggregate under sealed and unsealed conditions, Cement and Concrete Composites, 2008(Accepted).
- [8] Henkensiefken, R., P. Briatka, D. Bentz, T. Nantung, and J. Weiss, Plastic shrinkage cracking in internally cured mixtures made with pre-wetted lightweight aggregate, Concrete International, 2009(Submitted).
- [9] A.S El- Dieb , Self curing concrete, water retention, hydration and moisture.
- [10] IS: 516-1959 (Reaffirmed 1999). Indian Standard code of practice for Methods of tests for strength of concrete. Bureau of Indian Standards, New Delhi.
- [11] IS: 5816-1970. Indian Standard code of practice for Methods of tests for splitting tensile strength of concrete cylinders. Bureau of Indian Standards, New Delhi.
- [12] IS: 10262-1982. (Reaffirmed 2004). Indian Standard code of practice for recommended guidelines for concrete mix design. Bureau of Indian Standards, New Delhi.
- [13] IS:12269-1982. (Reaffirmed 2004). Indian Standard specifications for 53 grade ordinary Portland cement. Bureau of Indian Standards, New Delhi.